

PRODUCT DESCRIPTION

SSS100M is a two component 100% solids clear epoxy specifically designed for use with metallic floor systems. It offers exceptional flow and self-leveling characteristics, along with extended working time to achieve movement and metallic effects not typically found in flooring epoxies. 100M contains additives that prevent bubble formation and drive bubbles to the surface leaving metallic floors with a smooth, bubble free and glass-like appearance.

RECOMMENDED FOR

Recommended for warehouses, kitchens, basements, garages, restrooms, or any other interior space in which a decorative floor is desired.

PHYSICAL PROPERTIES

Solids by weight	100%
Solids by volume	100%
Volatile Organic Content	Less than 2 g/l
Standard Colors	Clear - gardner color 1-2
Recommended film thickness	16-18 mils
Packaging information	3 gallon kits (2.95 gallons net approximately) 15 gallon kits (14.75 gallons net approximately)
Shelf life	1 year in unopened containers
Finish characteristics	Gloss (>70 @ 60 degrees @ glossmeter)
Abrasion resistance	Taber abraser CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 36 mg loss
Flexural strength	7,400 psi @ ASTM D790
Compressive strength	11,200 psi @ ASTM D695
Mix ratio	9.0 pounds part A (.99 gallons) to 4.15 pounds part B (.49 gallons) (volumes approx.)
Adhesion	350 psi @ elcometer (concrete failure, no delamination)
Viscosity	Mixed = < 700 cps (typical)
DOT classifications	Part A "not regulated" Part B "CORROSIVE LIQUID N.O.S., 8, UN11760, PGIII"
Tensile strength	7,600 psi @ ASTM D638
Coverage per gallon	80 sq. ft. per gallon for metallic epoxy - 20 mils
Primer	Recommended: SSS300
Topcoat	Recommended - Apply one coat of SSS500 aliphatic urethane for enhanced chemical and abrasion resistance. Optional - depending on the environment, an aliphatic urethane can provide additional chemical resistance and UV resistance. Discuss this topic with your sales representative.
Application Temperature	55-90 degrees F
Ultimate Elongation	4.1%
Gardner Variable Impactor	50 inch pounds direct - passed
Hardness	Shore D = 81

CURE SCHEDULE

Pot life - 1 1/2 gallon volume	20-30 minutes @ 70° F
Tack free (dry to touch)	10-12 hours @ 70° F
Recoat or topcoat	12-18 hours @ 70° F
Light foot traffic	16-24 hours @ 70° F
Full cure (heavy traffic)	2-7 days @ 70° F

CHEMICAL RESISTANCE

REAGENT	RATING
Butanol	C
Xylene	C
1, 1, 1 Trichloroethane	B
MEK	A
Methanol	A
Ethyl Alcohol	C
Skydrol	B
10% Sodium Hydroxide	E
50% Sodium Hydroxide	D
10% Sulfuric Acid	C
70% Sulfuric Acid	A
10% HC1 (aq)	C
5% Acetic Acid	B

Rating Key:

- A - not recommended
- B - 2 hour term splash spill
- C - 8 hour term splash spill
- D - 72 hour immersion
- E - long term immersion

NOTE: extensive chemical resistance information is available through your sales representative.

LIMITATIONS

*Color stability or gloss may be affected by environmental conditions such as high humidity, chemical exposure, UV exposure or exposure to lighting such as sodium vapor lights.

*Color clarity may vary from batch to batch. Therefore, use only product from the same batch for an entire job.

*This product is not UV color stable. Clear aliphatic urethane topcoats reduce (UV light) color changes.

*Substrate temperature must be 5°F above dew point.

*For best results, apply with a 3/8" shed resistant nap roller.

*All new concrete must be cured for at least 30 days prior to application.

*Apply a suitable primer before using this product.

*See reverse side for application instructions.

*Physical properties are typical values and not specifications.

*See reverse side for limitations of our liability and warranty.

MIXING AND APPLICATION INSTRUCTIONS (SSS100M)

1. PRODUCT STORAGE

Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 90 degree F. Low temperatures or temperature fluctuations may cause crystallization.

2. SURFACE PREPARATION

The most suitable surface preparation would be a fine brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause dis-bonding.

3. PRODUCT MIXING

This product has a mix ratio of 9.0# part A to 4.15# part B. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. We highly recommend that the kits not be broken down unless suitable weighing equipment is available. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the primed substrate. Improper mixing may result in product failure.

4. PRIMING

A suitable primer should be used before applying this product. See the front side of this technical data for primer information. If a primer is not used, more porous substrates may cause outgassing and possible surface defects.

5. PRODUCT APPLICATION

The mixed material can be applied by brush or roller. However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating. This product can be used with various colored sand in a broadcast system or other suitable aggregate can be used in conjunction with this product to achieve a variety of color and application patterns. When using as a broadcast binder, always evaluate performance parameters with a test area which is dependent on aggregate size and thickness, prior to application. When using in conjunction with metallic pigments, for best results pre-mix the pigment into the Part A side before adding the Part B. Contact your representative for details as necessary.

6. RECOAT OR TOPCOATING

If you opt to recoat or topcoat this product, you must first be sure that the coating has tacked off before recoating. Always remember that colder temperatures will require more cure time for the product before recoating or top-coating can commence. Before recoating or top-coating, check the coating to insure no epoxy blushes were developed (a whitish, greasy film or de-glossing). If a blush is present, it must be removed prior to top-coating or recoating. Many aliphatic urethanes and polyaspartics are compatible for use as a topcoat for this product as well as multiple coats of this product.

7. CLEANUP

Use xylol.

8. FLOOR CLEANING

Caution! Some cleaners may affect the color. Test each cleaner in a small area. If no ill effects are noted, you can continue to clean with the product and process tested.

9. RESTRICTIONS

Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM. COPYRIGHT 2/28/20